


SUPPO 9 Volt Block mit 200 mAh bei 100 mA Last



SUPPO-9V1-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 25.07.2009 22:04
Discharge Rate: 0,10 A
Starting Voltage: 9,97 V
Ending Voltage: 7,00
Total Time (hh:mm:ss): 2:09:25
Tested Capacity: 0,216 Ah

SUPPO-9V2-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 27.07.2009 11:42
Discharge Rate: 0,10 A
Starting Voltage: 10,15 V
Ending Voltage: 7,00
Total Time (hh:mm:ss): 2:11:15
Tested Capacity: 0,218 Ah

SUPPO-9V3-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 27.07.2009 13:57
Discharge Rate: 0,10 A
Starting Voltage: 10,01 V
Ending Voltage: 7,00
Total Time (hh:mm:ss): 2:08:54
Tested Capacity: 0,215 Ah

SUPPO 9 Volt Block mit 200 mAh bei 100 mA Last

SUPPO-9V4-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 28.07.2009 11:02
Discharge Rate: 0,10 A
Starting Voltage: 10,04 V
Ending Voltage: 6,99
Total Time (hh:mm:ss): 2:12:09
Tested Capacity: 0,220 Ah

SUPPO-9V6-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 29.07.2009 13:07
Discharge Rate: 0,10 A
Starting Voltage: 10,05 V
Ending Voltage: 6,99
Total Time (hh:mm:ss): 2:09:46
Tested Capacity: 0,217 Ah

SUPPO-9V8-:

Description: 7 NiMH cells, 0,2 Ah @ 0,10A
Started At: 29.07.2009 13:07
Discharge Rate: 0,10 A
Starting Voltage: 10,05 V
Ending Voltage: 6,99
Total Time (hh:mm:ss): 2:09:46
Tested Capacity: 0,217 Ah